

Optical Properties of $(\text{SrMnO}_3)_n/(\text{LaMnO}_3)_{2n}$ Superlattices: An Insulator-to-Metal Transition Observed in the Absence of Disorder

Monday, 23 July 2012 20:00 (2 hours)

A. Perucchi¹, L. Baldassarre¹, A. Nucara², P. Calvani², C. Adamo³, D.G. Schlom³,
P. Orgiani⁴, L. Maritato⁴, S. Lupi⁵

1) Sincrotrone Trieste, Area Science Park, I-34012 Trieste, Italy

2) CNR-SPIN and Dipartimento di Fisica, Università Sapienza, P.le A. Moro 2, I-00185
Rome, Italy

3) Department of Materials Science and Engineering, Cornell University, Ithaca, New York
14853-1501, USA

4) CNR-SPIN and Dipartimento di Matematica ed Informatica, Università di Salerno,
Baronissi, I-84081 Salerno, Italy

5) CNR-IOM and Dipartimento di Fisica, Università di Roma La Sapienza, Piazzale Aldo Moro 2, I-00185 Rome,
Italy

We measure the optical conductivity, $\sigma_1(\omega)$, of $(\text{SrMnO}_3)_n/(\text{LaMnO}_3)_{2n}$ superlattices (SL) for $n=1, 3, 5$, and 8 and $10 < T < 400$ K. Data show a T-dependent insulator to metal transition (IMT) for $n=3$, driven by the softening of a polaronic mid-infrared band. At $n=5$ that softening is incomplete, while at the largest-period $n=8$ compound the MIR band is independent of T and the SL remains insulating. One can thus first observe the IMT in a Manganite system in the absence of the disorder due to chemical doping. Unsuccessful reconstruction of the SL optical properties from those of the original bulk materials suggests that $(\text{SrMnO}_3)_n/(\text{LaMnO}_3)_{2n}$ heterostructures give rise to a novel electronic state.

Primary author: PERUCCHI, Andrea (ELETTRA - Sincrotrone Trieste)

Presenter: PERUCCHI, Andrea (ELETTRA - Sincrotrone Trieste)

Session Classification: Poster Session 1

Track Classification: Metal-Insulator Systems